

**AEROSPACE
MATERIAL
SPECIFICATION****AMS 2451/9A**

Issued	2002-01
Revised	2007-05
Reaffirmed	2011-04
Superseding AMS 2451/9	

Plating, Brush, Zinc-Nickel
Low Hydrogen Embrittlement

RATIONALE

This specification was issued as part of the SAE Five Year Review process.

1. SCOPE**1.1 Purpose**

This specification covers the requirements for brush plating of zinc-nickel by electrodeposition.

1.2 Application

This process has been used typically to improve corrosion resistance of steel parts operating under 500 °F (260 °C) as-plated or under 250 °F (121 °C) when chromate treated, to repair zinc-nickel deposits and to repair damaged or worn parts, but usage is not limited to such applications.

1.3 Classification

Type 1 - As-plated

Type 2 - With supplementary surface treatment

1.3.1 Unless a specific type is specified, Type 1 shall be supplied.

1.4 Safety - Hazardous Materials

See AMS 2451.

2. APPLICABLE DOCUMENTS

See AMS 2451.

3. TECHNICAL REQUIREMENTS

See AMS 2451.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS2451/9A>**

SAE WEB ADDRESS:

<http://www.sae.org>

3.1 Procedure

- 3.1.1 Zinc-nickel alloy plate shall be electrodeposited from low-hydrogen-embrittlement brush plating solution in accordance with processing instructions from the solution manufacturer. When Type 2 plating is specified, the supplementary coating shall be applied using brush, spray or dip.
- 3.1.2 When specified by the cognizant engineering organization, the hydrogen embrittlement relief baking requirement of AMS 2451 may be waived. See 8.4.

3.2 Properties

3.2.1 Composition

The zinc-nickel alloy deposit shall contain 6 to 20% nickel and the balance essentially zinc, determined by a method agreed upon by purchaser and processor.

3.2.2 Nickel Strike

When applied, shall be not less than 0.00005 inch (1.3 µm) thick.

3.2.3 Corrosion Resistance

The requirements of AMS 2451 shall apply except that salt spray exposure time shall be 500 hours \pm 1. Specimens shall be plated to a thickness of 0.0004 to 0.0007 inch (10 to 18 µm).

3.2.3.1 Type 2 parts shall show no evidence of corrosion products after 96 hours and no evidence of basis metal corrosion after 500 hours exposure to salt spray corrosion test in accordance with ASTM B 117.

3.2.4 The hardness, stress, and heat resistance tests of AMS 2451 section 3.4.2 are not applicable to this deposit.

3.2.5 Hydrogen Embrittlement

The plating process shall not cause hydrogen embrittlement in steel parts, determined in accordance with 4.2.

4. QUALITY ASSURANCE PROVISIONS

See AMS 2451.

4.1 When specified by the cognizant engineering organization, the hydrogen embrittlement relief testing of 4.2 may be waived. See 8.4.

4.2 Hydrogen Embrittlement Test

Test shall be in accordance with the requirements of ASTM F 519 using three Type 1a.1 notched specimens stressed in tension under constant load, unless a different specimen is specified by the purchaser. For test purposes, the plating thickness shall be 0.0003 to 0.0006 inch (8 to 15 µm) measured on the smooth section of the specimen, but with visual plating at the root of the notch.

4.3 Periodic Tests

Hydrogen embrittlement (4.2) is a periodic test and shall be performed at least once each month that parts are processed. Tests of cleaning and plating solutions are periodic tests and shall be performed at a frequency established by the processor unless frequency of testing is specified by cognizant engineering organization.

5. PREPARATION FOR DELIVERY

See AMS 2451.