

# AEROSPACE MATERIAL SPECIFICATION

**AMS 3656D**  
Superseding AMS 3656C

Issued 1-15-60  
Revised 10-1-84

## POLYTETRAFLUOROETHYLENE EXTRUSIONS Normal Strength, As Sintered, Radiographically Inspected

### 1. SCOPE:

- 1.1 Form: This specification covers polytetrafluoroethylene resin in the form of extruded rods, tubes, and shapes.
- 1.2 Application: Primarily for mechanical parts, such as seals, back-up rings, and bearings, requiring chemical inertness up to 260°C (500°F). When dimensional stability is important, extrusions may be stress-relief annealed but best results will be obtained by machining parts almost to size, stress-relief annealing, and taking a thin, finishing cut.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D149 - Dielectric Breakdown Voltage and Dielectric Strength of Solid Electrical Insulating Materials at Commercial Power Frequencies

ASTM D638 - Tensile Properties of Plastics

ASTM D792 - Specific Gravity and Density of Plastics by Displacement

**REAFFIRMED**  
10-91

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

## 2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

## 3. TECHNICAL REQUIREMENTS:

3.1 Material: The product shall be extruded from polytetrafluoroethylene powder without admixture of fillers, pigments, or adulterants and shall be sintered.

3.2 Color: May vary from white to mottled gray or brown. Small gray, brown, or black spots shall not in themselves be unacceptable.

3.3 Properties: Extrusions shall conform to the following requirements; tests shall be performed on the extrusions supplied and in accordance with specified test methods, insofar as practicable:

3.3.1 Tensile Strength at  $23^{\circ}\text{C} \pm 1$  ( $73^{\circ}\text{F} \pm 2$ ), min: 4.5.1

### 3.3.1.1 Rods and Shapes

Nominal Diameter or Distance Between Parallel Sides		
Inches	Millimetres	
Up to 0.500, excl	Up to 12.50, excl	1600 psi (11 MPa)
0.500 to 1.500, incl	12.50 to 37.50, incl	1700 psi (11.5 MPa)
Over 1.500	Over 37.50	1800 psi (12.5 MPa)

3.3.1.2 Tubes, All Sizes 1600 psi (11 MPa)

3.3.2 Elongation at  $23^{\circ}\text{C} \pm 1$  ( $73^{\circ}\text{F} \pm 2$ ), min: 4.5.1

### 3.3.2.1 Rods and Shapes

Nominal Diameter or Distance Between Parallel Sides		
Inches	Millimeters	
Up to 0.500, excl	Up to 12.50, excl	100%
0.500 to 1.500, incl	12.50 to 37.50, incl	125%
Over 1.500	Over 37.50	150%

3.3.2.2 Tubes, All Sizes 100%

3.3.3 Specific Gravity at 23°/23°C (73°/73°F):

ASTM D792  
Add 2 drops  
of wetting  
agent to the  
water

## 3.3.3.1 Rods and Shapes

Nominal Diameter or Distance Between Parallel Sides		
Inches	Millimetres	
Up to 0.500, excl	Up to 12.50, excl	2.12 - 2.17
0.500 to 1.500, incl	12.50 to 37.50, incl	2.13 - 2.18
Over 1.500	Over 37.50	2.14 - 2.19

## 3.3.3.2 Tubes, All Sizes

2.12 - 2.17

3.3.4 Dielectric Strength, Short Time Test, min:

4.5.2

## 3.3.4.1 Rods and Shapes

Nominal Diameter or Distance Between Parallel Sides		
Inches	Millimetres	
Up to 0.500, excl	Up to 12.50, excl	600 V per mil (23,600 V/mm)
0.500 to 1.500, incl	12.50 to 37.50, incl	650 V per mil (25,600 V/mm)
Over 1.500	Over 37.50	700 V per mil (27,550 V/mm)

## 3.3.4.2 Tubes, All Sizes

600 V per mil (23,600 V/mm)

3.4 Quality: Extrusions, as received by purchaser, shall be uniform in quality  
Ø and condition, smooth, and free from foreign materials and from  
imperfections detrimental to usage of the extrusions.

3.4.1 The product shall be radiographically inspected. Radiographic procedures  
and standards for acceptance shall be as agreed upon by purchaser and  
vendor.

3.5 Tolerances: Unless otherwise specified, the following tolerances apply at  
23° - 30°C (73° - 86°F):

## 3.5.1 Rods and Shapes:

TABLE I

Nominal Diameter or Distance Between Parallel Sides Inches	Tolerance, Inch plus only
Up to 0.250, incl	0.008
Over 0.250 to 0.500, incl	0.016
Over 0.500 to 0.750, incl	0.020
Over 0.750 to 1.000, incl	0.024
Over 1.000 to 1.250, incl	0.030
Over 1.250 to 1.500, incl	0.038
Over 1.500 to 1.750, incl	0.046
Over 1.750 to 2.000, incl	0.052
Over 2.000 to 2.250, incl	0.068
Over 2.250 to 2.500, incl	0.076

TABLE I (SI)

Nominal Diameter or Distance Between Parallel Sides Millimetres	Tolerance, Millimetres plus only
Up to 6.25, incl	0.20
Over 6.25 to 12.50, incl	0.40
Over 12.50 to 18.75, incl	0.50
Over 18.75 to 25.00, incl	0.60
Over 25.00 to 31.25, incl	0.75
Over 31.25 to 37.50, incl	0.95
Over 37.50 to 43.75, incl	1.15
Over 43.75 to 50.00, incl	1.30
Over 50.00 to 56.25, incl	1.75
Over 56.25 to 62.50, incl	1.95

## 3.5.2 Tubes:

TABLE II

Nominal OD or ID Inches	ID Tolerance, Inch minus only	OD Tolerance, Inch plus only
Over 0.187 to 2.000, incl	0.062	0.062

TABLE II (SI)

Nominal OD or ID Millimetres	ID Tolerance, Millimetres minus only	OD Tolerance, Millimetres plus only
Over 4.75 to 50.00, incl	1.55	1.55

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of extrusions shall supply all  
Ø samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the extrusions conform to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to all technical  
Ø requirements of this specification are classified as acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical  
Ø requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of extrusions to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when  
Ø requested, preproduction extrusions shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

#### 4.3 Sampling: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient extrusions shall be taken at random from  
Ø each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 A lot shall be all extrusions of the same configuration made from the  
Ø same batch of compound in one production run and presented for vendor's inspection at one time.

4.3.1.2 An inspection lot shall be not more than 200 lb (90 kg) of extrusions.  
Ø A lot may be packaged or delivered in small quantities under the basic lot approval provided lot identification is maintained.

4.3.1.3 When a statistical sampling plan and acceptance quality level (AQL) have  
Ø been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.  
Ø

## 4.4 Approval:

- 4.4.1 Sample extrusions shall be approved by purchaser before extrusions for production use are supplied, unless such approval be waived by purchaser. Results of tests on production extrusions shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production extrusions which are essentially the same as those used on the approved sample extrusions. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material or processing, or both, and when requested, sample extrusions. Production extrusions made by the revised procedure shall not be shipped prior to the receipt of reapproval.

## 4.5 Test Methods:

- 4.5.1 Tensile Strength and Elongation: Shall be determined in accordance with ASTM D638 using a testing speed of 2 in. (50 mm) per min. and measuring elongation over a 2 in. (50 mm) gage length. The test specimen for rod, and for shapes where size permits, shall conform to Fig 1 of this specification except that rods 0.250 in. (6.25 mm) and under in diameter may be tested in full cross-section.
- 4.5.2 Dielectric Strength: Shall be determined in accordance with ASTM D149 on specimens 0.040 in.  $\pm$  0.001 (1.00 mm  $\pm$  0.02) thick. The test shall be conducted under oil using 0.062-in. (1.55-mm) diameter corrosion-resistant steel electrodes with rounded edges. If flash-over is a problem on small diameter rod or on shapes, specimens shall be prepared by drilling holes from opposite ends of a piece of product, leaving a web 0.040 in.  $\pm$  0.001 (1.00 mm  $\pm$  0.02) thick in the middle of the specimen. Electrodes shall be the same as used for the wafer specimen and shall be inserted in the holes in the specimen.

## 4.6 Reports:

- 4.6.1 The vendor of extrusions shall furnish with each shipment a report showing the results of tests to determine conformance to the tensile strength, elongation, specific gravity, and dielectric strength requirements and stating that the extrusions conform to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3656D, lot number, vendor's compound number, form and size or part number, and quantity.

4.6.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 3656D, contractor or other direct supplier of extrusions, supplier's compound number, part number, and quantity. When extrusions for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of extrusions to determine conformance to the requirements of this specification and shall include in the report either a statement that the extrusions conform or copies of laboratory reports showing the results of tests to determine conformance.

4.7 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the extrusions may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the extrusions represented and no additional testing shall be permitted. Results of all tests shall be reported.

## 5. PREPARATION FOR DELIVERY:

### 5.1 Packaging and Identification:

5.1.1 Packaging shall be accomplished in such a manner as to ensure that the extrusions, during shipment and storage, will not be permanently distorted and will be protected against damage from exposure to weather or any other normal hazard.

5.1.2 Each package shall be permanently and legibly marked with not less than the following information:

POLYTETRAFLUOROETHYLENE EXTRUSIONS

Normal Strength, As Sintered, Radiographically Inspected

AMS 3656D

SIZE OR PART NUMBER \_\_\_\_\_

LOT NUMBER \_\_\_\_\_

PURCHASE ORDER NUMBER \_\_\_\_\_

QUANTITY \_\_\_\_\_

MANUFACTURER'S IDENTIFICATION \_\_\_\_\_

5.1.3 Packages of extrusions shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the extrusions to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.1.4 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-794, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.1.1 and 5.1.3 will be acceptable if it meets the requirements of Level C.