

AEROSPACE MATERIAL SPECIFICATION



AMS 3892/1B

Issued NOV 1972
Revised OCT 1992
Reaffirmed MAY 2005

Superseding AMS 3892/1A

Tow or Yarn, Carbon Fibers
For Structural Composites
GF 400 (2758) Tensile Strength, 33 (228) Tensile Modulus

1. SCOPE:

1.1 Form:

This specification covers one type of continuous multifilament carbon fibers in the form of a tow or yarn (when twisted). The weight per unit length of the tow or yarn is governed by the filament count which is identified by the supplier's grade or material designation.

1.2 Classification:

Carbon tow or yarn, derived from a polyacrylonitrile precursor, with typical 400 ksi (2758 MPa) tensile strength and 33 Msi (228 GPa) tensile modulus for use in general purpose structural composites requiring high tensile strength and moderate modulus of elasticity in tension.

2. APPLICABLE DOCUMENTS:

See AMS 3892.

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the carbon tow or yarn described herein shall consist of this document and the latest issue of the basic specification.

3.2 Storage Life:

The product shall be readily strippable from the spool and the filaments spreadable when tested at any time up to six months from date of receipt by purchaser provided it has been stored at room temperature in the original closed container.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2005 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
http://www.sae.org

SAE WEB ADDRESS:

3.3 Properties:

Shall conform to the requirements shown in Table 1. The requirements of 3.3.1 and 3.3.2 apply to the average of the number of determinations indicated in the basic specification but no individual value shall be less than 90% of the specified minimum average unless due to an obvious testing problem, in which case a substitute specimen may be tested.

TABLE 1 - Properties

Paragraph	Property	Requirement
3.3.1	Tensile Strength, minimum	380 ksi (2620 MPa)
3.3.2	Tensile Modulus	
	minimum	32 Msi (221 GPa)
	maximum	36 Msi (248 GPa)
3.3.3	Ultimate Elongation	1.1%
	minimum	
3.3.4	Mass per unit length	Preproduction Value $\pm 5\%$
3.3.5	Finish Content, maximum	2% by weight
3.3.6	Density	0.061 to 0.066 pound per cubic inch (1.69 to 1.83 g/cm ³)
3.3.7	Yarn Twist (when applicable),	
	nominal	0.4 turn per inch (15 turns/m)
	maximum	0.8 turn per inch (30 turns/m)

4. QUALITY ASSURANCE PROVISIONS:

See 3892.

5. PREPARATION FOR DELIVERY:

See AMS 3892.