

FIBERBOARD, HARL-PRESSED, STRUCTURAL

1. SCOPE:

1.1 Form: This specification covers hard-pressed fiberboard in the form of flat panels.

1.2 Application: Primarily for parts requiring moderate strength, such as panelling and sheathing of shipping containers.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D1037 - Evaluating the Properties of Wood-Base Fiber and Particle Panel Materials

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-W-3448 - Wallboard, Packaging of

3. TECHNICAL REQUIREMENTS:

3.1 Material and Fabrication: The product shall consist of wood fibers physically or chemically separated, felted, and heavily compressed to produce the properties specified in 3.2, using the natural wood lignins or other suitable adhesive as a bonding agent, in accordance with the following:

3.1.1 Wood Species: Shall be one or a combination of the following:

Spruce	Cottonwood
Fir	Willow
Poplar	Pine
Gumwood	Redwood
Aspen	Douglas Fir

3.1.2 Laminating: Panels 5/16 in. (7.9 mm) and under in nominal thickness shall be one solid sheet. Panels over 5/16 in. (7.9 mm) in nominal thickness shall be laminated from thinner sheets. Panels 1/4 in. (6.4 mm) and over in nominal thickness and requiring both faces smooth may be laminated from thinner sheets. Bonding of laminated panels shall be accomplished with a thermosetting synthetic resin glue resistant to formation and growth of molds and fungi.

3.1.3 Chemical Treatment: Panels may be chemically treated to improve strength and abrasion resistance and to reduce moisture absorption.

3.2 Properties: Fiberboard shall conform to the following requirements, determined in accordance with ASTM D1037, Part B, and, except for density, shall be reported as the average of all values for each test:

3.2.1 Density: Shall be not lower than 31 lb per cu ft (497 kg/m<sup>3</sup>).

3.2.2 Tensile Strength:

3.2.2.1 Parallel to Surface: Shall be not lower than 3500 psi (24 MPa); strength shall be approximately equal in all surface directions.

3.2.2.2 Perpendicular to Surface: Shall be not lower than 150 psi (1.03 MPa).

3.2.3 Modulus of Rupture: Shall be not lower than 7000 psi (48.3 MPa).

### 3.2.4 Water Resistance:

3.2.4.1 Water Absorption, by Weight: Shall be not greater than the following as applicable to the surface finish specified:

<u>Nominal Thickness</u>		<u>Absorption, %</u>	
<u>Inch</u>	<u>Millimetres</u>	<u>Smooth One Side (S1S)</u>	<u>Smooth Both Sides (S2S)</u>
1/12	2.1	30	--
1/10	2.5	20	25
1/8	3.2	15	20
3/16	4.8	12	18
1/4	6.4	10	12
5/16	7.9	8	11
3/8	9.5	8	10

3.2.4.2 Thickness Swelling: Shall be not greater than the following as applicable to the surface finish specified:

<u>Nominal Thickness</u>		<u>Thickness Increase, %</u>	
<u>Inch</u>	<u>Millimetres</u>	<u>Smooth One Side (S1S)</u>	<u>Smooth Both Sides (S2S)</u>
1/12	2.1	25	--
1/10	2.5	16	20
1/8	3.2	11	16
3/16	4.8	10	15
1/4	6.4	8	11
5/16	7.9	8	10
3/8	9.5	8	9

3.2.4.3 Water resistance requirements for fiberboard over 3/8 in. (9.5 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3 Workability: Fiberboard shall not crack, split, chip, or delaminate when drilled, sawed, or nailed perpendicularly to the surface.

3.4 Quality: Fiberboard, as received by purchaser, shall be sound and free from foreign materials and from imperfections detrimental to usage of the fiberboard. Panels shall be flat and shall have at least one face smooth; laminated panels shall be smooth on both surfaces.

3.5 Tolerances: Shall be as follows:

3.5.1 Thickness: Shall be as specified in Table I, measured in accordance with ASTM D1037:

TABLE I

Nominal Thickness Inches	Actual Thickness Inches
1/12	0.070 - 0.090
1/10	0.091 - 0.100
1/8	0.115 - 0.155
3/16	0.165 - 0.205
1/4	0.210 - 0.265
5/16	0.290 - 0.335
3/8	0.350 - 0.400
7/16	0.410 - 0.460
1/2	0.475 - 0.525
5/8	0.600 - 0.650
11/16	0.660 - 0.710
3/4	0.725 - 0.775
13/16	0.785 - 0.835
7/8	0.850 - 0.900
1	0.975 - 1.025
1-1/8	1.115 - 1.155

TABLE I (SI)

Nominal Thickness Millimetres	Actual Thickness Millimetres
2.1	1.78 - 2.29
2.5	2.31 - 2.54
3.2	2.92 - 3.94
4.8	4.19 - 5.21
6.4	5.33 - 6.73
7.9	7.37 - 8.51
9.5	8.89 - 10.16
11.1	10.41 - 11.68
12.7	12.06 - 13.34
15.9	15.24 - 16.51
17.5	16.76 - 18.03
19.0	18.42 - 19.68
20.6	19.94 - 21.21
22.2	21.59 - 22.86
25.4	24.76 - 26.04
28.6	28.32 - 29.34

3.5.2 Length and Width: Nominal length shall be as ordered and nominal width shall be 4 ft (1.22 m) or 5 ft (1.52 m), as ordered. Tolerance on length and width shall be  $\pm 1/64$  in. per ft ( $\pm 1.3$  mm/m) of linear dimension.

3.5.3 Squareness: The difference in lengths of the two face diagonals of a panel shall be not greater than 1/64 in. per ft (1.3 mm/m) of length of panel. Opposite edges of panels shall not vary more than 1/8 in. (3.2 m) in length.

3.5.4 Edge Straightness: Edges of panels shall be straight within 1/16 in. per ft (5.2 mm/m) of length or width, determined by stretching a string or wire from one corner to the adjacent corner and measuring the greatest distance between the string or wire and the panel edge being tested.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of fiberboard shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the fiberboard conforms to the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for material and fabrication (3.1), tensile strength (3.2.2), water resistance (3.2.4), and tolerances (3.4) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of fiberboard to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling: Shall be as follows; a lot shall be all panels of one size manufactured in one continuous production run and presented for vendor's inspection at one time. A lot may be packaged in smaller quantities and delivered under the basic lot approval provided lot identification is maintained.

4.3.1 For Acceptance Tests: In accordance with ASTM D1037.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

#### 4.4 Approval:

4.4.1 Sample fiberboard shall be approved by purchaser before fiberboard for production use is supplied, unless such approval be waived by purchaser. Results of tests on production fiberboard shall be essentially equivalent to those on the approved sample.