



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4164E

Superseding AMS 4164D

Issued 6-30-60
Revised 10-16-78

UNS A92024

ALUMINUM ALLOY EXTRUSIONS
4.4Cu - 1.5Mg - 0.60Mn (2024-T3510)
Stress-Relief Stretched, Unstraightened

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of extruded bars, rods, wire, shapes, and tubing.
- 1.2 Application: Primarily for parts subject to excessive warpage during machining due to residual stresses, and for parts requiring high strength and whose fabrication does not normally involve welding. Certain design and processing procedures may cause these extrusions to be susceptible to stress-corrosion cracking; ARP 823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) and Aerospace Recommended Practices (ARP) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2205 - Tolerances, Aluminum-Base and Magnesium-Base Alloy Extrusions
AMS 2350 - Standards and Test Methods
AMS 2355 - Quality Assurance Sampling and Testing of Aluminum-Base and Magnesium-Base Alloys, Wrought Products (Except Forgings and Forging Stock) and Flash Welded Rings
AMS 2630 - Ultrasonic Inspection

2.1.2 Aerospace Recommended Practices:

ARP 823 - Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products

- 2.2 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.2.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.2.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355:

| | min | max |
|-------------------------|-----------|------|
| Copper | 3.8 | 4.9 |
| Magnesium | 1.2 | 1.8 |
| Manganese | 0.30 | 0.9 |
| Iron | -- | 0.50 |
| Silicon | -- | 0.50 |
| Zinc | -- | 0.25 |
| Zirconium + Titanium | -- | 0.20 |
| Titanium | -- | 0.15 |
| Chromium | -- | 0.10 |
| Other Impurities, each | -- | 0.05 |
| Other Impurities, total | -- | 0.15 |
| Aluminum | remainder | |

- 3.2 Condition: Solution heat treated in accordance with MIL-H-6088 and stress relieved by stretching to produce a nominal permanent set of 1-1/2%, but not less than 1% nor more than 3%.

- 3.2.1 Extrusions shall receive no straightening after stretching.

- 3.2.2 Extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within the dimensional tolerances.

- 3.3 Properties: Extrusions shall conform to the following requirements, determined in accordance with AMS 2355:

- 3.3.1 Tensile Properties: Shall be as specified in Table I, Table II, and 3.3.1.3.

- 3.3.1.1 Bars, Rods, Wire, and Shapes:

TABLE I

| Nominal Dimensions | | Tensile Strength psi, min | Yield Strength at 0.2% Offset psi, min | Elongation in 2 in. or 4D %, min |
|---------------------------------|--|---------------------------------|--|--|
| Diameter or Thickness Inches | Cross Sectional Area Square Inches | | | |
| Up to 0.249, incl | All areas | 57,000 | 42,000 | 12 |
| Over 0.249 to 0.749, incl | All areas | 60,000 | 44,000 | 12 |
| Over 0.749 to 1.499, incl | All areas | 65,000 | 46,000 | 10 |
| Over 1.499 | Up to 25, incl | 70,000 | 52,000 | 10 |
| Over 1.499 | Over 25 to 32, incl | 68,000 | 48,000 | 8 |

TABLE I (SI)

| Nominal Dimensions | | Tensile Strength MPa, min | Yield Strength at 0.2% Offset MPa, min | Elongation in 50 mm or 4D %, min |
|--------------------------------------|---|---------------------------------|--|--|
| Diameter or Thickness Millimetres | Cross Sectional Area Square Centimetres | | | |
| Up to 6.32, incl | All areas | 393 | 290 | 12 |
| Over 6.32 to 19.02, incl | All areas | 414 | 303 | 12 |
| Over 19.02 to 38.07, incl | All areas | 448 | 317 | 10 |
| Over 38.07 | Up to 161, incl | 483 | 359 | 10 |
| Over 38.07 | Over 161 to 206, incl | 469 | 331 | 8 |

3.3.1.2 Round Tubing:

TABLE II

| Nominal Wall Thickness and Area Inches | Tensile Strength psi, min | Yield Strength at 0.2% Offset psi, min | Elongation in 2 in. or 4D %, min |
|--|---------------------------------|--|--|
| Up to 0.249, incl, all areas | 57,000 | 42,000 | 10 |
| Over 0.249 to 0.749, incl, all areas | 60,000 | 44,000 | 10 |
| Over 0.749 to 1.499, incl, all areas | 65,000 | 46,000 | 10 |
| Over 1.499 | | | |
| Area up to 25 sq in., incl | 70,000 | 48,000 | 10 |
| Area over 25 to 32 sq in., incl | 68,000 | 46,000 | 8 |

TABLE II (SI)

| | Tensile Strength MPa, min | Yield Strength at 0.2% Offset MPa, min | Elongation in 50 mm or 4D %, min |
|---|---------------------------------|--|--|
| Up to 6.32, incl, all areas | 393 | 290 | 10 |
| Over 6.32 to 19.02, incl, all areas | 414 | 303 | 10 |
| Over 19.02 to 38.07, incl, all areas | 448 | 317 | 10 |
| Over 38.07 | | | |
| Area up to 161 cm ² , incl | 483 | 331 | 10 |
| Area over 161 to 206 cm ² , incl | 469 | 317 | 8 |

3.3.1.3 Tensile property requirements for sizes over 1.499 in. (38.07 mm) in nominal diameter or distance between parallel sides or in nominal wall thickness or over 32 sq in. (206 cm²) in nominal cross-sectional area shall be as agreed upon by purchaser and vendor.

3.3.2 Hardness: Should be not lower than 100 HB/10/500, 100 HB/14.3/1000, or 106 HB/10/1000, but the extrusions shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4 Quality: Extrusions, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the extrusions.

3.4.1 When specified, extrusions shall be subjected to ultrasonic inspection in accordance with AMS 2630. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.5 Tolerances: Unless otherwise specified, tolerances shall conform to all applicable requirements of AMS 2205.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of extrusions shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the extrusions conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), tensile properties (3.3.1), ultrasonic inspection (3.4.1) when specified, and tolerances (3.5) are classified as acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for hardness (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355.

4.4 Reports:

4.4.1 The vendor of extrusions shall furnish with each shipment three copies of a report stating that the extrusions conform to the chemical composition and other technical requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size or section identification number, and quantity.

4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of extrusions, part number, and quantity. When extrusions for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of extrusions to determine conformance to the requirements of this specification, and shall include in the report a statement that the extrusions conform, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.5 Resampling and Retesting: Shall be in accordance with AMS 2355.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Extrusions shall be identified as follows:

5.1.1 Each straight bar, rod, and tube 0.500 in. (12.70 mm) and over in OD or least width of flat surface and each straight shape with configuration allowing access to a flat surface at least 0.500 in. (12.70 mm) wide recessed not more than 1/8 in. (3.2 mm) below the outline of the shape shall be marked in a row of characters recurring at intervals not greater than 3 ft (914 mm) with the alloy number and temper, AMS 4164 or applicable Federal or Military specification designation, and manufacturer's identification. The characters shall be of such size as to be clearly legible, shall be applied using a suitable marking fluid, and shall be sufficiently stable to withstand normal handling. The markings shall have no deleterious effect on the extrusions or their performance.

5.1.2 All straight extrusions other than those of 5.1.1 shall be securely bundled, boxed, or secured on lifts and identified by two durable tags marked with the information of 5.1.1 and attached, not farther than 2 ft (610 mm) from each end, to the extrusions in each bundle, box, or lift.