

SUPERSEDED



400 COMMONWEALTH DRIVE WARRENDALE PA 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 4282E

Issued 6- 2- 42
Revised 10- 1- 81

ALUMINUM ALLOY CASTINGS, PERMANENT MOLD
4.5Cu - 2.5Si (B195-T6)
Solution and Precipitation Treated

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of 4-26-68. It is recommended that this specification not be specified for new designs.

This cover sheet should be attached to the "E" revision of the subject specification.

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of 10-1-81. By this action, subject specification number and title will be deleted from the active specification index of Aerospace Material Specifications.

SAENORM.COM : Click to view the full PDF of AMS4282E

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade for their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 4282E

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Avenue, New York 17, N.Y.

Issued 6-1-42
Revised 6-15-59

ALUMINUM ALLOY CASTINGS, PERMANENT MOLD 4.5Cu - 2.5Si (B195-T6) Solution and Precipitation Treated

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. COMPOSITION:

Copper	4.0 - 5.0
Silicon	2.0 - 3.0
Iron	1.2 max
Manganese	0.30 max
Zinc	0.30 max
Titanium	0.20 max
Magnesium	0.05 max
Other impurities, total	0.30 max
Aluminum	remainder

3. CONDITION: Solution and precipitation heat treated.

4. TECHNICAL REQUIREMENTS:

4.1 Casting: Castings shall be produced in lots from metal conforming to Section 2. Metal remelted from previously analyzed ingot may be poured directly into castings. Furnace or ladle additions of small amounts of grain refining elements or alloys are permissible. Unless otherwise agreed upon by purchaser and vendor, molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or until the composition of a sample taken after the last addition to the melt has been found to conform to Section 2.

4.1.1 A melt shall be the metal withdrawn from a batch furnace charge of 2000 lb or less as melted for pouring castings or, when permitted by the purchaser, a melt shall be 4000 lb or less of metal withdrawn from one continuous furnace in not more than 8 consecutive hours.

4.1.2 A lot shall consist of castings poured from a single melt in not more than 8 consecutive hours.

4.2 Test Specimens: Tensile test specimens, and chemical analysis specimens when required, shall be cast and, when requested, shall be supplied with the castings.

4.2.1 Tensile Test Specimens: Shall be cast with each lot of castings, shall be standard (0.5 in. diameter at the reduced parallel section), and shall be cast to size in permanent molds. Metal for the specimens shall be part of the melt which is used for the castings. If the metal for castings is given any treatment, such as fluxing or cooling and reheating, the metal for the specimens shall be a portion of the metal so treated, and during such treatment, shall be heated to the same maximum temperature and held for approximately the same length of time as the molten metal for castings.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry is entirely voluntary. The rules do not require anyone to adhere to any SAE standard or recommendation, practice, and no commitment is to be made by anyone to conform to any technical report, in formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. For specific users of the report, the user should refer to the original report for a listing of the patents." The user should refer to the original report for a listing of the patents.

4.2.2 Chemical Analysis Specimens: When required by purchaser, shall be cast from each melt and shall be of size and shape agreed upon by purchaser and vendor.

4.3 Heat Treatment: All castings and tensile test specimens representing them shall be heat treated as follows:

4.3.1 Tensile test specimens from each lot, together with production castings, shall be heated to the proper temperature and for the proper time for solution treatment and quenched at a rate not faster than that produced by immersion in water which is boiling at the time of immersion. At least one set of tensile test specimens shall be put into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than 3 hours.

4.3.2 Tensile test specimens from each lot, together with production castings, shall, after solution treatment as in 4.3.1, be heated uniformly to not lower than 290 F, held at heat for not less than 1.5 hr, and cooled in air. At least one set of tensile test specimens shall be put into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than 3 hours.

4.4 Tensile Properties:

4.4.1 Cast Test Specimens:

Tensile Strength, psi	35,000	min
Yield Strength at 0.2% Offset or at 0.0083 in. in 2 in. Extension Under Load (E = 10,300,000), psi	22,000	min
Elongation, % in 2 in.	2.0	min

4.4.2 Specimens Cut from Castings:

4.4.2.1 When tensile properties of actual castings are determined for acceptance, not less than 4, and preferably 10, tensile test specimens shall be cut from thick and thin sections. The average value of all specimens selected shall conform to the following:

Tensile Strength, psi	26,500	min
Yield Strength at 0.2% Offset or at 0.0072 in. in 2 in. Extension Under Load (E = 10,300,000), psi	16,500	min
Elongation (Round Specimens), % in 4D	0.5	min

4.4.2.1.1 Conformance to these requirements may be used as basis for acceptance of castings.

4.4.2.2 When specified on the order, tensile test specimens taken in locations indicated on the drawing, from a casting chosen at random to represent the lot, shall have the properties indicated on the drawing for each specimen.

4.5 Hardness of Castings: Except at sprues and risers, the castings shall have hardness of Brinell 80 - 110 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or Brinell 85 - 115 using 1000 kg load and 10 mm ball.

5. QUALITY:

- 5.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.
- 5.2 Radiographic and other quality standards shall be as agreed upon by purchaser and vendor.
- 5.3 Unless otherwise specified, castings shall be produced under radiographic control. This shall consist of radiographic examination of castings until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number, and of production castings as necessary to ensure maintenance of satisfactory quality.
- 5.4 Castings shall not be repaired by plugging, welding, or other methods, without written permission from purchaser.
- 5.5 Castings shall not be impregnated, chemically treated, or coated to prevent leaking, unless specified or allowed by written permission which states the method to be used. Impregnated castings shall be marked IMP.

6. REPORTS:

- 6.1 Unless otherwise specified, the vendor of castings shall furnish with each shipment three copies of a report of the results of tensile tests on test specimens from each lot and a statement that the chemical composition of castings conforms to the requirements of this specification. This report shall include the purchase order number, lot number, material specification number, part number, and quantity.
- 6.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, that vendor shall inspect each shipment or lot of castings to determine conformance to the requirements of this specification, and shall include in the report a statement that the castings conform, or shall include copies of laboratory reports showing the results of tests to determine conformance.

7. IDENTIFICATION: Unless otherwise specified, castings shall be identified in accordance with the latest issue of AMS 2804 including the lot number and heat treatment batch number.

8. APPROVAL:

- 8.1 To assure uniformity of quality, sample castings from new or reworked molds shall be approved by purchaser, unless such approval be waived.
- 8.2 Vendor shall use the same foundry practices and the same heat treating procedures for production castings as for approved sample castings. If necessary to make any change, vendor shall notify purchaser prior to the first shipment of castings incorporating such change.

9. REJECTIONS: Castings not conforming to this specification or to authorized modifications will be subject to rejection.