

# AEROSPACE MATERIAL SPECIFICATION

**SAE AMS 5340**

**REV. D**

Issued 1964-01  
Revised 1997-03  
Reaffirmed 2011-10

Superseding AMS 5340C

(R) Steel, Corrosion Resistant, Investment Castings  
14Cr - 4.25Ni - 2.25Mo - 0.25Cb - 3.25Cu  
Homogenization and Solution Heat Treated

UNS J92240

## RATIONALE

This document has been reaffirmed to comply with the SAE 5-year Review policy.

### 1. SCOPE:

#### 1.1 Form:

This specification covers a corrosion-resistant steel in the form of investment castings.

#### 1.2 Application:

These castings have been used typically for parts requiring corrosion resistance and strength up to 1000 °F (538 °C), but usage is not limited to such applications.

### 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

#### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2360	Room Temperature Tensile Properties of Castings
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:** Tel: 877-606-7323 (inside USA and Canada)  
Tel: +1 724-776-4970 (outside USA)  
Fax: 724-776-0790  
Email: CustomerService@sae.org  
http://www.sae.org

**SAE values your input. To provide feedback  
on this Technical Report, please visit  
<http://www.sae.org/technical/standards/AMS5340D>**

**SAE WEB ADDRESS:**

## 2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E 1444	Magnetic Particle Examination

## 2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-H-6875	Heat Treatment of Steels, Process for
MIL-STD-453	Inspection, Radiographic
MIL-STD-2175	Castings, Classification and Inspection of
MIL-STD-6866	Inspection, Liquid Penetrant
QQ-P-35	Passivation Treatments for Corrosion-Resistant Steel

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

Castings shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser (See 8.2.1 and 8.2.2).

TABLE 1 - Composition

Element	min	max
Carbon	--	0.06
Manganese	--	0.70
Silicon	0.50	1.00
Phosphorus	--	0.020
Sulfur	--	0.025
Chromium	13.50	14.25
Nickel	3.75	4.75
Columbium	0.15	0.35
Molybdenum	2.00	2.50
Copper	3.00	3.50
Tantalum	--	0.05
Nitrogen	--	0.05

3.1.1 Vendor may test for any element not otherwise listed in Table 1 and include this analysis in the report of 4.5. Limits of acceptability may be specified by purchaser (See 8.2.3).

3.1.2 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

### 3.2 Melt Practice:

Castings and specimens shall be poured at casting vendor's facility either from a melt (See 8.2.4) of a master heat, or directly from a master heat (See 8.2.5).

3.2.1 Revert (gates, sprues, risers, and rejected castings) may be used only in the preparation of master heats; revert shall not be remelted directly, without refining, for pouring of castings.

3.2.2 Portions of two or more qualified master heats (See 3.4.2) may be melted together and poured into castings using a procedure authorized by purchaser (See 8.2.6).

3.2.3 If modifications, such as alloy additions or replenishments, are made by the vendor at remelt, vendor shall have a written procedure acceptable to purchaser which defines the controls, test, and traceability criteria for both castings and separately-cast specimens. Control factors of 4.4.2.2 shall apply.

### 3.3 Condition:

Castings and tensile specimens shall be delivered in the solution heat treated condition, except as specified in 3.3.1 and 3.3.2.

3.3.1 When acceptable to purchaser, castings and specimens shall be solution heat treated twice.

3.3.2 When acceptable to purchaser, castings and specimens shall be homogenization heat treated prior to solution heat treatment.

### 3.4 Test Specimens:

Specimens shall be either separately-cast, integrally-cast (See 8.2.7), or machined from a casting, and shall conform to 3.2.

3.4.1 If specimens are separately-cast, vendor shall have a written procedure acceptable to purchaser. Control factors of 4.4.2.2 shall apply.

3.4.2 Each master heat shall be qualified by evaluation of chemical and tensile specimens.

3.4.2.1 If alloy additions or replenishments are made at remelt as in 3.2.3, frequency of sampling and testing used by the vendor for qualification to 3.4.2 shall be acceptable to purchaser.

3.4.3 Chemical Analysis Specimens: Shall be of any convenient size and shape.

3.4.4 Tensile Specimens: Shall be of standard proportions in accordance with ASTM E 8 or ASTM E 8M (See 8.3) with 0.250 inch (6.35 mm) diameter at the reduced parallel gage section.

3.4.4.1 Separately-cast and integrally-cast specimens may be either cast to size, or cast oversize and subsequently machined to 0.250 inch (6.35 mm) diameter.

3.4.4.2 When integrally-cast specimens and specimens machined from a casting are specified, specimen size and location shall be agreed upon by purchaser and vendor (See 8.2.8 and 8.5).

### 3.5 Heat Treatment:

Castings and representative tensile specimens shall be heat treated in accordance with MIL-H-6875, except as specified in 3.5.1 and 3.5.2.

#### 3.5.1 Castings and Tensile Specimens:

3.5.1.1 Homogenization Heat Treatment: When acceptable to purchaser in accordance with 3.3.2, heat in a neutral or slightly reducing atmosphere to  $2100^{\circ}\text{F} \pm 25$  ( $1149^{\circ}\text{C} \pm 14$ ), hold at heat for not less than 90 minutes, and cool as required to below  $70^{\circ}\text{F}$  ( $21^{\circ}\text{C}$ ).

3.5.1.2 Solution Heat Treatment: Heat in a neutral or slightly reducing atmosphere to  $1900^{\circ}\text{F} \pm 25$  ( $1038^{\circ}\text{C} \pm 14$ ), hold at heat for 1 hour per inch (25 mm) of section thickness but not less than 30 minutes, and cool as required to below  $70^{\circ}\text{F}$  ( $21^{\circ}\text{C}$ ).

3.5.2 Response to Heat Treatment: After heat treatment in accordance with 3.5.1, tensile specimens shall be heat treated as follows for subsequent testing to demonstrate response to heat treatment:

3.5.2.1 Precipitation Heat Treatment: Heat to  $1100^{\circ}\text{F} \pm 15$  ( $593^{\circ}\text{C} \pm 8$ ), hold at heat for not less than 4 hours, and cool in air.

3.5.3 Tensile specimens used for master heat qualification may be heat treated separately from castings.

### 3.6 Properties:

Conformance shall be based upon testing separately-cast specimens unless purchaser specifies integrally-cast specimens or specimens machined from a casting.

3.6.1 Room Temperature Tensile Properties: Shall be as specified in Table 2 or Table 3, determined in accordance with ASTM E 8 or ASTM E 8M (See 8.3), after heat treatment in accordance with 3.5.2. Properties other than those listed may be defined as specified in AMS 2360.

3.6.1.1 Separately-Cast Specimens: Shall be as shown in Table 2.

TABLE 2 - Minimum Room Temperature Tensile Properties

Property	Value
Tensile Strength	150 ksi (1034 MPa)
Yield Strength at 0.2% Offset	130 ksi ( 896 MPa)
Elongation in 4D	10%
Reduction of Area	25%

3.6.1.2 Integrally-Cast and Machined-from-Casting Specimens: Shall be as shown in Table 3.

TABLE 3 - Minimum Room Temperature Tensile Properties

Property	Value
Tensile Strength	140 ksi (965 MPa)
Yield Strength at 0.2% Offset	130 ksi (896 MPa)
Elongation in 4D	6%
Reduction of Area	15%

3.6.2 Hardness: Shall be as follows, determined in accordance with ASTM E 18:

3.6.2.1 Castings: Castings, heat treated to the condition of 3.5.1, shall have hardness not higher than 36 HRC.

3.6.2.2 Castings and Representative Tensile Specimens: Castings and representative tensile specimens, heat treated to the condition of 3.5.2, shall have hardness not lower than 30 HRC.

3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings. Castings shall be free of cracks, laps, hot tears, and cold shuts, and free of scale and other process-induced surface contamination which would obscure defects.

3.7.1.1 Unless otherwise specified, castings shall be sufficiently cleaned such that, after passivation by purchaser, the castings shall meet the corrosion test requirement of QQ-P-35.

- 3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of each casting part number until foundry manufacturing controls in accordance with 4.4.2 have been established. Additional radiography shall be conducted in accordance with the frequency of inspection specified by purchaser, or as necessary to ensure continued maintenance of internal quality.
- 3.7.2.1 Radiographic inspection shall be conducted in accordance with MIL-STD-453 or other method specified by purchaser.
- 3.7.3 When specified, castings shall be subjected to additional nondestructive testing as follows:
- 3.7.3.1 Fluorescent penetrant inspection in accordance with MIL-STD-6866 or other method specified by purchaser.
- 3.7.3.2 Magnetic particle inspection in accordance with ASTM E 1444 or other method specified by purchaser.
- 3.7.4 Acceptance standards for radiographic, fluorescent penetrant, magnetic particle, visual, and other inspection methods shall be agreed upon by purchaser and vendor (See 8.2.8). MIL-STD-2175 may be used to specify acceptance standards (casting grade) and frequency of inspection (casting class).
- 3.7.4.1 When acceptance standards are not specified, Grade C of MIL-STD-2175 shall apply for each applicable inspection method.
- 3.7.5 Castings shall not be peened, plugged, impregnated, or welded unless authorized by purchaser.
- 3.7.5.1 When authorized by purchaser, welding in accordance with AMS 2694 or other welding program acceptable to purchaser may be used.

#### 4. QUALITY ASSURANCE PROVISIONS:

##### 4.1 Responsibility for Inspection:

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to specified requirements.

##### 4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.6.1), hardness of castings (3.6.2.1, and 3.6.2.2 if castings are precipitation heat treated by vendor), and quality (3.7) are acceptance tests and shall be performed as specified in 4.3.

- 4.2.2 Periodic Tests: Hardness of specimens (3.6.2.2), corrosion resistance (3.7.1.1), and radiographic soundness (3.7.2) are periodic tests and shall be performed at a frequency selected by vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: All technical requirements are preproduction tests and shall be performed on sample castings (4.3.2), when a change in control factors occurs (4.4.2.2), and when purchaser deems confirmatory testing to be required.

#### 4.3 Sampling and Testing:

The minimum testing performed by vendor shall be in accordance with the following:

- 4.3.1 One chemical analysis specimen or a casting from each master heat shall be tested for conformance with Table 1; if 3.4.2.1 applies, test frequency shall be acceptable to purchaser.
- 4.3.2 One preproduction casting in accordance with 4.4 shall be tested to the requirements of the casting drawing and to all technical requirements.
- 4.3.2.1 Dimensional inspection sample quantity shall be as specified by purchaser.
- 4.3.3 Tensile tests shall be conducted to determine conformance with Table 2 or Table 3. Sampling and test frequency is dependent upon the type and origin of specimen specified by purchaser (See 3.4.4) or selected by vendor (See 4.3.3.4). When 3.4.2.1 applies, test frequency shall be acceptable to purchaser.
- 4.3.3.1 For separately-cast specimens in the fully heat treated condition (See 3.3 and 3.5.2), one specimen from each master heat shall be tested to Table 2.
- 4.3.3.2 For integrally-cast specimens in the fully heat treated condition (See 3.3 and 3.5.2), two specimens from each lot (See 8.2.9) shall be randomly selected and tested to Table 3.
- 4.3.3.3 For specimens machined from a casting, one casting shall be randomly selected from each lot and tested in the fully heat treated condition (See 3.3 and 3.5.2), at locations shown on the engineering drawing for conformance with Table 3.
- 4.3.3.3.1 When size and location of specimens are not shown, two test specimens shall be tested, one from the thickest section and one from the thinnest section. Once established under 4.4.2.2, test locations may be changed only as agreed upon by purchaser and vendor.
- 4.3.3.4 When acceptable to purchaser, specimens machined from a casting may be used in lieu of both separately-cast and integrally-cast specimens, and integrally-cast specimens may be used in lieu of separately-cast specimens. In each case, the resultant properties must conform to the requirements of 3.6 for that type of specimen.
- 4.3.3.4.1 When specimens are selected for test as in 4.3.3.4 from an origin other than that specified by purchaser, vendor shall include in the report of 4.5 a description of the origin of the specimen that was tested.

- 4.3.3.5 When casting size, section thickness, gating method, or other factors do not permit conformance with 4.3.3.2 or 4.3.3.3, sampling and testing shall be agreed upon by purchaser and vendor.
- 4.3.4 Castings shall be inspected in accordance with 3.7 to the methods, frequency, and acceptance standards specified by purchaser.
- 4.3.5 Castings shall be tested for hardness to determine conformance to 3.6.2.1. Unless otherwise specified by purchaser, one casting per lot shall be hardness tested.
- 4.3.5.1 In event of failure, the entire lot shall be 100% inspected or reheat treated in accordance with 4.6.2.
- 4.4 Approval:
  - 4.4.1 Sample casting(s) from new or reworked master patterns produced under the casting procedure of 4.4.2 shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.
  - 4.4.2 For each casting part number, vendor shall establish parameters for process control factors that will consistently produce castings and test specimens meeting the requirements of the casting drawing and this specification. These parameters shall constitute the approved casting procedure and shall be used for production of subsequent castings and test specimens. If necessary to make any change to these parameters, vendor shall submit a statement of the proposed change for purchaser reapproval. When requested, vendor shall also submit test specimens, sample castings, or both to purchaser for reapproval.
    - 4.4.2.1 Production castings produced prior to receipt of purchaser's approval shall be at vendor's risk.



- 4.4.2.2 Control factors for producing castings and separately-cast specimens include, but are not limited to, the following factors. Supplier's procedures shall identify tolerances, ranges, and/or control limits, as applicable. Control factors for separately-cast specimens must generally represent, but need not be identical to, those factors used for castings (See 3.2.3 and 3.4.1):

Composition of ceramic cores, if used  
Arrangement and number of patterns in the mold (including integrally-cast specimens, if applicable)  
Size, shape, and location of gates and risers  
Mold refractory formulation  
Grain refinement methods, if applicable  
Mold back up material (weight, thickness, or number of dips)  
Type of furnace, atmosphere, and charge for melting  
Mold preheat and metal pouring temperatures  
Fluxing or deoxidation procedure  
Replenishment and alloy addition procedures, if applicable  
Time molten metal is in furnace  
Solidification and cooling procedures  
Cleaning operations (mechanical and chemical)  
Heat treatment  
Straightening  
Final inspection methods  
Location and size of integrally-cast specimens and specimens machined from a casting, if applicable

- 4.4.2.2.1 Any of the control factors for which parameters are considered proprietary by vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

- 4.4.2.2.1.1 Unless otherwise agreed upon by purchaser and vendor, purchaser shall be entitled to review proprietary control factor details and coding at vendor's facility.

#### 4.5 Reports:

The vendor of castings shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements. This report shall include the purchase order number, master heat identification, heat treat/lot identification, AMS 5340D, part number, quantity, and source of tensile property specimens (See 4.3.3.4.1).

#### 4.6 Resampling and Retesting:

If results of a valid test fail to meet specified requirements, two additional specimens in accordance with 4.3 from the same master heat, modified melt (See 3.2.3), or lot, as applicable, shall be tested for each nonconforming characteristic. Results of each additional test, and the average of results of all tests (original and retests) shall meet specified requirements; otherwise, the master heat or lot shall be rejected. Results of all tests shall be reported.