

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5361B

Issued 10-1-50

Revised 12-1-53

STEEL CASTINGS, SAND AND CENTRIFUGAL, CORROSION AND HEAT RESISTANT
18Cr - 13Ni - 2.1Mo

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for parts and assemblies requiring both corrosion and heat resistance up to 1600 F. At high temperatures, strength of this steel is slightly higher than, and oxidation resistance is similar to, that of 18-8 types.
3. COMPOSITION:

Carbon	0.15 - 0.25
Manganese	2.0 max
Silicon	1.0 max
Phosphorus	0.04 max
Sulfur	0.04 max
Chromium	17.0 - 20.0
Nickel	12.0 - 15.0
Molybdenum	1.75 - 2.5

4. CONDITION: Solution heat treated, unless otherwise specified.

5. TECHNICAL REQUIREMENTS:

- 5.1 Solution Heat Treatment: Castings shall be solution heat treated by heating to 1950 F \pm 50, holding at heat for at least 1 hr, and cooling in air.

- 5.2 Hardness: Castings shall have hardness not higher than Brinell 211 or equivalent.

6. QUALITY:

- 6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned. Unless otherwise specified, metallic shot or grit shall not be used for final cleaning.
- 6.2 When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides and other defects.
- 6.3 Unless otherwise specified, castings shall be produced under radiographic control.
- 6.4 Inspection standards and procedures shall be as agreed upon by purchaser and vendor.
- 6.5 Castings shall not be repaired by plugging, welding or other methods without written permission from purchaser.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."