

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5389

Issued 3-1-48

Revised

ALLOY CASTINGS, SAND, CORROSION AND HEAT RESISTANT
Nickel Base 17Mo - 15Cr - 6Fe - 5W

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

2. APPLICATION: Parts and assemblies, such as tail pipe and exhaust cone fittings, requiring high strength up to approximately 1500 F, and oxidation resistance up to 1800 F.

3. COMPOSITION:

| | |
|-----------------------|---------------|
| Carbon | 0.15 max |
| Manganese | 1.00 max |
| Silicon | 1.00 max |
| Molybdenum | 15.00 - 18.00 |
| Chromium | 14.00 - 17.00 |
| Iron | 4.50 - 7.00 |
| Tungsten | 3.75 - 5.25 |
| Vanadium | 0.20 - 0.40 |
| Cobalt, if determined | 2.50 max |
| Nickel plus Cobalt | remainder |

4. CONDITION: Annealed, unless otherwise specified.

5. TECHNICAL REQUIREMENTS: (a) Annealing.-- Castings shall be annealed by heating to $2225 F + 25$, holding at that temperature for not less than 30 minutes and cooling in air.

(b) Hardness.-- Castings shall have hardness not higher than Brinell 221 or equivalent.

6. QUALITY: (a) Castings shall be uniform in quality and condition, sound and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.

(b) When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides and other defects.

(c) Unless otherwise specified, castings shall be produced under radiographic control.

(d) Inspection standards and procedures shall be as agreed upon by purchaser and vendor.

(e) Castings shall not be repaired by plugging, welding or other methods without written permission from the purchaser.

Section 1 of the SAE Technical Board rules provides that: "All technical reports, including standards, specifications, and practices recommended, are advisory only. Their use in industry or trade is entirely voluntary. There is no agreement to adhere to a standard or recommended practice, and no commitment to cost or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents that may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."