

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.

29 West 39th Street

New York City

AMS 5532B

Issued 9-1-47

Revised 6-15-50

ALLOY SHEET, CORROSION AND HEAT RESISTANT Iron Base - 20Cr - 20Ni - 20Co - 3Mo - 2W - 1Cb

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Parts, such as welded nozzle diaphragm assemblies, burner liner parts, tail pipes, exhaust cone assemblies, and other parts requiring high strength up to approximately 1500 F, and oxidation resistance up to 1800 F.
3. COMPOSITION:

	Check Analysis		
	Under Min	Or	Over Max
Carbon	0.08	-	0.16
Manganese	1.00	-	2.00
Silicon	1.00	max	—
Phosphorus	0.040	max	—
Sulfur	0.030	max	—
Chromium	20.00	-	22.50
Nickel	19.00	-	21.00
Cobalt	18.50	-	21.00
Molybdenum	2.50	-	3.50
Tungsten	2.00	-	3.00
Columbium + Tantalum	0.75	-	1.25
Nitrogen	0.10	-	0.20
Iron	Remainder		

4. CONDITION: Unless otherwise specified, material shall be hot rolled, annealed, and pickled, having a surface appearance as close as possible to a commercial corrosion resistant steel No. 2D finish; standards for acceptance and rejection shall be as agreed upon by purchaser and vendor.

5. TECHNICAL REQUIREMENTS:

5.1 Physical Properties:

Tensile Strength, psi 100,000 - 140,000
Elongation, % in 2 in. 40 min

Note: For widths 9 inches and over, tensile test specimens shall be taken with the axis perpendicular to the direction of rolling. For widths less than 9 inches, tensile test specimens shall be taken with the axis parallel to the direction of rolling.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment is made to or by any person to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider any patent rights which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2 Bending: Material shall withstand, without cracking, bending at room temperature through the angle indicated below around a diameter equal to the bend factor times the nominal thickness of the material, with axes of bends both perpendicular and parallel to the direction of rolling.

Nominal Thickness Inch	Angle, Degrees Min	Bend Factor
Under 0.050	180	1
0.050 and over	180	2

5.3 Stress-Rupture Test at 1500 F: Sheet shall be capable of meeting the following requirements:

5.3.1 A tensile test specimen, maintained at 1500 F + 5 while an axial load of 18,000 psi is applied continuously, shall not rupture in less than 24 hours. The test shall be continued, after the 24 hours, until the specimen ruptures, either maintaining the same load or increasing the load to not over 25,000 psi as necessary to produce rupture. In either case, the elongation after rupture, measured at room temperature, shall be not less than 10% in 2 in.

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2242 as applicable. Thickness and flatness tolerances shall be as specified below:

7.1 Thickness: Table I.

7.2 Flatness: Table VI.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each thickness from each lot to determine conformance to the physical property and bending requirements of this specification. This report shall include the purchase order number, lot number, material specification number, thickness, size, and quantity from each lot. A lot shall be considered to be any number of individual furnace heats of approximately the same composition which are processed as a unit.

8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.