

G-31-40

G-31-45

G-65-09

NOTICE OF
ADOPTION

ADOPTION NOTICE 1
17 March 1989 for
AMS 5763B
1 October 1987
SUPERSEDING
AMS 5763A
30 October 1981

AMS 5763B was adopted on 17 March 1989 and is approved for use by the Department of Defense (DoD). Copies of this document are stocked at the Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120 for issue to DOD activities only. Other Government Agencies, contractors, private concerns, or other requestors must obtain the document from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

Title of Document: STEEL BARS, FORGINGS, AND TUBING, AND RINGS,
CORROSION RESISTANT 15Cr - 6.5Ni - 0.75Mo - 0.50 (Cb
+ Ta) - 1.5Cu Solution Heat Treated

Date of Specific Issued Adopted: 1 October 1987

Releasing Non-Government Standards Body: SAE

Custodians:
Air Force - 11
Army - MR
Navy - AS

Military Coordinating Activity
Air Force - 11

(Project No: 9510-0691)

FSC 9510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

G-31-40

G-31-45

G-65-09

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 5763B

Issued 11-15-72

Revised 10-1-87

Superseding AMS 5763A

STEEL BARS, FORGINGS, AND TUBING, AND RINGS, CORROSION RESISTANT

15Cr - 6.5Ni - 0.75Mo - 0.50 (Cb + Ta) - 1.5Cu

Solution Heat Treated

UNS S45000

1. SCOPE:

1.1 Form: This specification covers a corrosion-resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings.

1.2 Application: Primarily for parts requiring corrosion resistance approximating that of steels of the 18-8 types and high strength exceeding that of the 12 Cr martensitic types up to 700°F (370°C). This steel can be used in the solution heat treated condition and is capable of being precipitation heat treated to tensile strengths as high as 180,000 psi (1240 MPa). Although this steel is relatively immune to stress-corrosion cracking, reference should be made to ARP 1110 for recommended practices to minimize such conditions.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2241 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

MAM 2241 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2243 - Tolerances, Corrosion and Heat Resistant Steel Tubing

MAM 2243 - Tolerances, Metric, Corrosion and Heat Resistant Steel Tubing

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.1 (Cont'd.)

- AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2303 - Aircraft Quality Steel Cleanliness, Martensitic Corrosion Resistant Steels, Magnetic Particle Inspection Procedure
- MAM 2303 - Aircraft Quality Steel Cleanliness, Martensitic Corrosion Resistant Steels, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock
- AMS 2374 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Forgings and Forging Stock
- AMS 2375 - Control of Forgings Requiring First Article Approval
- AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
- AMS 2808 - Identification, Forgings
- AMS 7490 - Rings, Flash Welded, Corrosion and Heat Resistant Austenitic Steels and Austenitic-Type Alloys

2.1.2 Aerospace Recommended Practices:

- ARP 1110 - Minimizing Stress Corrosion Cracking in Heat Treatable Wrought Low Alloy and Martensitic Corrosion Resistant Steels

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM A370 - Mechanical Testing of Steel Products
- ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

- MIL-H-6875 - Heat Treatment of Steel, Process for

2.3.2 Military Standards:

- MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrochemical or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.05
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.030
Sulfur	--	0.030
Chromium	14.00 - 16.00	
Nickel	6.00 - 7.00	
Molybdenum	0.50 - 1.00	
Columbium + Tantalum	8 x C - 0.75	
Copper	1.25 - 1.75	

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Bars, Wire, Mechanical Tubing, Forgings, and Flash Welded Rings: Solution heat treated.

- 3.2.1.1 Bars:

- 3.2.1.1.1 Rounds: Centerless ground after solution heat treatment.

- 3.2.1.1.2 Squares, Hexagons, and Flats: Hot finished, solution heat treated, and descaled or cold drawn after solution heat treatment and descaling, as ordered.

- 3.2.1.2 Wire: Cold drawn after solution heat treatment.

- 3.2.1.3 Mechanical Tubing: Cold finished and solution heat treated.

- 3.2.1.4 Flash Welded Rings: Shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS 7490.

- 3.2.2 Stock for Forging or Flash Welded Rings: As ordered by the forging or flash welded ring manufacturer.

- 3.3 Heat Treatment: Bars, wire, forgings, mechanical tubing, and flash welded rings shall be solution heat treated by heating to $1900^{\circ}\text{F} + 25$ ($1040^{\circ}\text{C} + 15$), holding at heat for not less than 1 hr, and cooling rapidly. Furnace surveys and calibration of temperature controllers and recorders shall be in accordance with MIL-H-6875.

3.4 Properties: The product shall conform to the following requirements; hardness and tensile testing shall be conducted in accordance with ASTM A370:

3.4.1 Bars, Wire, Forgings, Mechanical Tubing, and Flash Welded Rings: Shall be as follows on product 8.0 in. (200 mm) and under in least nominal cross-sectional dimension; requirements for product over 8.0 in. (200 mm) in nominal least cross-sectional dimension shall be as agreed upon by purchaser and vendor:

3.4.1.1 As Solution Treated:

3.4.1.1.1 Tensile Properties:

3.4.1.1.1.1 Bars, Forgings, Tubing, and Flash Welded Rings:

Tensile Strength, min	125,000 psi (860 MPa)
Yield Strength at 0.2% Offset, min	95,000 psi (655 MPa)
Elongation in 4D, min	10%
Reduction of Area, min	40%

3.4.1.1.1.2 Wire: Not higher than 165,000 psi (1135 MPa) or equivalent hardness.

3.4.1.1.2 Hardness: Shall be as follows:

3.4.1.1.2.1 Bars: Not higher than 311 HB, or equivalent, determined midway between surface and center.

3.4.1.1.2.2 Tubing, Flash Welded Rings, and Forgings: Not higher than 311 HB, or equivalent.

3.4.1.2 After Precipitation Heat Treatment: The product shall have the following properties after being precipitation heat treated by heating to $900^{\circ}\text{F} + 15$ ($480^{\circ}\text{C} + 8$), holding at heat for not less than 4 hr, and cooling in air:

3.4.1.2.1 Tensile Properties: Shall be as follows:

Tensile Strength, min	180,000 psi (1240 MPa)
Yield Strength at 0.2% Offset, min	170,000 psi (1170 MPa)
Elongation in 4D, min	10%
Reduction of Area, min	40%

3.4.1.2.2 Hardness: Should be not lower than 363 HB, or equivalent, but the product shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.1.2.1 are met.

3.4.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated as in 3.3 and 3.4.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2. If specimens taken from the stock after heat treatment as in 3.3 and 3.4.1.2, conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.4.3 Stock for Flash Welded Rings: Specimens taken from the stock after heat treatment as in 3.3 and 3.4.1.2 shall conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2.

3.5 Quality:

3.5.1 When specified, steel shall conform to AMS 2303 or MAM 2303.

3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.2.1 Forgings shall have substantially uniform macrostructure. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.5.2.2 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings, showing no evidence of re-entrant flow.

3.6 Sizes: Except when exact lengths or multiples of exact lengths are ordered, straight bars, wire, and tubing will be acceptable in mill lengths of 6 - 20 ft (2 - 6 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 ft (3 m).

3.7 Tolerances: Shall conform to all applicable requirements of the following:

3.7.1 Bars and Wire: AMS 2241 or MAM 2241.

3.7.2 Mechanical Tubing: AMS 2243 or MAM 2243.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties (3.4.1.1) and hardness (3.4.1.1.2) of each lot of bars, wire, forgings, mechanical tubing, and flash welded rings as solution heat treated.

4.2.1.3 Tolerances (3.7) of bars, wire, and mechanical tubing.

4.2.2 Periodic Tests: Tests to determine conformance to the following requirements are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser:

4.2.2.1 Tensile properties (3.4.1.2.1) and hardness (3.4.1.2.2) of each lot of bars, wire, forgings, mechanical tubing, and flash welded rings after precipitation heat treatment.

4.2.2.2 Ability of forging stock (3.4.2) and stock for flash welded rings (3.4.3) to develop required properties.

4.2.3 Preproduction Tests: Tests of forgings to determine conformance to all applicable technical requirements of this specification when AMS 2375 is specified are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a forging to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction forgings shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, and Stock for Flash Welded Rings: AMS 2371.

4.3.2 Forgings and Forging Stock: AMS 2374.

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of bars, wire, forgings, mechanical tubing, and flash welded rings shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and the results of tests on each lot to determine conformance to the other acceptance tests and, when performed, to the periodic test requirements of this specification. This report shall include the purchase order number, heat number, AMS 5763B, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5.2 The vendor of stock for forging or flash welded rings shall furnish with each shipment a report showing the results of tests for chemical composition and, when specified, frequency-severity cleanliness rating of each heat. This report shall include the purchase order number, heat number, AMS 5763B, size, and quantity.