

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS 5860B

Issued 11-15-71
Revised 1-1-86

Superseding AMS 5860A

STEEL SHEET, STRIP, AND PLATE, CORROSION AND MODERATE HEAT RESISTANT
12Cr - 8.5Ni - 0.30 (Cb + Ta) - 1.1Ti - 2.0Cu
Vacuum Induction Melted and Vacuum Arc Consumable Electrode Remelted
1525°F (830°C) Solution Heat Treated UNS S45500

1. SCOPE:

1.1 Form: This specification covers a corrosion and moderate heat resistant steel in the form of sheet, strip, and plate.

1.2 Application: Primarily for parts requiring corrosion resistance and high strength in service up to 800°F (425°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2242 - Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
- MAM 2242 - Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Sheet, Strip, and Plate
- AMS 2248 - Chemical Check Analysis Limits, Wrought Corrosion and Heat Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
- AMS 2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure
- MAM 2300 - Premium Aircraft-Quality Steel Cleanliness, Magnetic Particle Inspection Procedure, Metric (SI) Measurement
- AMS 2350 - Standards and Test Methods
- AMS 2371 - Quality Assurance Sampling of Corrosion and Heat Resistant Steels and Alloys, Wrought Products Except Forgings and Forging Stock

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

- 2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.05
Manganese	--	0.50
Silicon	--	0.50
Phosphorus	--	0.025
Sulphur	--	0.025
Chromium	11.00 - 12.50	
Nickel	7.50 - 9.50	
Columbium + Tantalum	0.10 - 0.50	
Titanium	0.80 - 1.40	
Copper	1.50 - 2.50	
Molybdenum	--	0.50

- 3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2248.

- 3.2 Condition: The product shall be supplied in the following condition:

- 3.2.1 Sheet and Strip: Cold rolled, solution heat treated, and, unless solution heat treatment is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to the following commercial corrosion-resistant steel finishes:

- 3.2.1.1 Sheet: No. 2D finish.

- 3.2.1.2 Strip: No. 1 strip finish.

3.2.2 Plate: Hot rolled, solution heat treated, and descaled.

3.3 Heat Treatment: The product shall be solution heat treated plate
 Ø over 1.25 in. (31 mm) in nominal thickness shall be water quenched.

3.3.1 For product heat treated in a continuous process, the product shall be
 Ø solution heat treated by heating to 1650°F + 25 (900°C + 15), holding at heat for a time commensurate with thickness and the heating equipment and procedure used, and cooling in air.

3.4 Properties: The product shall conform to the following requirements; hardness, tensile, and bend testing shall be performed in accordance with ASTM A370:

3.4.1 As Solution Heat Treated:

3.4.1.1 Tensile Properties:

Tensile Strength, max 175,000 psi (1205 MPa)
 Yield Strength at 0.2% Offset, max 160,000 psi (1105 MPa)
 Elongation in 2 in. (50 mm) or 4D, min 3%

3.4.1.2 Hardness: Product 0.010 in. (0.25 mm) and over in nominal thickness should have hardness not higher than 35 HRC, or equivalent, but shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.1.1 are met.

3.4.1.3 Bending: Product 0.1875 in. (4.75 mm) and under in nominal thickness shall withstand, without cracking, free bending through an angle of 90 deg around a diameter equal to 2-1/2 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

3.4.2 After Precipitation Heat Treatment: The product shall have the following properties after being precipitation heat treated by heating to 950°F + 10 (510°C + 5), holding at heat for 4 hr + 0.25, and cooling in air:

3.4.2.1 Tensile Properties: Shall be as specified in Table I.

TABLE I

Nominal Thickness Inch	Tensile Strength psi, min	Yield Strength at 0.2% Offset, psi, min	Elongation in 2 in. or 4D %, min
Up to 0.020, incl	225,000	210,000	2
Over 0.020 to 0.062, incl	225,000	210,000	3
Over 0.062	225,000	210,000	4

TABLE I (SI)

Nominal Thickness Millimetres	Tensile Strength MPa, min	Yield Strength at 0.2% Offset, MPa, min	Elongation in 50 mm or 4D %, min
Up to 0.50, incl	1550	1450	2
Over 0.50 to 1.55, incl	1550	1450	3
Over 1.55	1550	1450	4

3.4.2.2 Hardness: Product 0.010 in. (0.25 mm) and over in nominal thickness should have hardness not lower than 44 HRC, or equivalent, but shall not be rejected on the basis of hardness if the tensile property requirements of 3.4.2.1 are met.

3.4.3 After Other Precipitation Heat Treatment: Properties after precipitation heat treatment at temperatures other than $950^{\circ}\text{F} \pm 10$ ($510^{\circ}\text{C} \pm 5$) shall be as agreed upon by purchaser and vendor.

3.5 Quality:

3.5.1 Steel shall be premium aircraft-quality conforming to AMS 2300 or MAM 2300; it shall be multiple melted using consumable electrode practice in the remelt cycle or shall be induction melted under vacuum.

3.5.2 The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6 Tolerances: Shall conform to all applicable requirements of AMS 2242 or MAM 2242.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties (3.4.1.1), hardness (3.4.1.2), and bending (3.4.1.3) of each lot as solution heat treated.