

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 6264

Issued 9-1-42
Revised

S T E E L
2 Ni .9 Cr .35 Mo (.15-.20 C)

1. ACKNOWLEDGMENT: A vendor must mention this specification number in all quotations and when acknowledging purchase orders.

2. FORM: Bars, billets, forgings, or as ordered.

3. COMPOSITION:

Individual Bar
Check Analysis
Over or Under

Carbon	0.15 - 0.20	0.01
Manganese	0.70 - 0.90	0.03
Phosphorus	0.040 max	0.005
Sulphur	0.040 max	0.005
Silicon	0.20 - 0.35	0.02
Nickel	2.0 - 2.5	0.07
Chromium	0.80 - 1.10	0.05
Molybdenum	0.30 - 0.40	0.03

4. GRAIN SIZE: 5 or finer, ASTM E19-39T, method a, unless otherwise ordered. A heat of steel predominately 5 or finer, with grains as large as 3, is permissible.

5. HARDENABILITY: Specimens with sections 1/8 inch and 3/4 inch in thickness, and not greater than 2 square inches in area, cut to represent an area half way between the center and outside of the bar or forging, shall be ground and copper plated, placed in a furnace which is at 1475°F and allowed to heat to 1475°F, held 25 minutes and quenched in commercial paraffin oil (100 S.U.V. at 100°F) at room temperature. The specimens shall have a hardness within the limits of Rockwell C 40-47.

6. CONDITION: (a) Bar stock must be supplied in a machineable condition with a hardness of not more than Brinell 229, unless otherwise ordered.

(b) Stock ordered for forging must be supplied in the condition and finished ordered by the forging manufacturer.

(c) forgings are to be supplied as ordered.

7. QUALITY: (a) This material must be aircraft quality. It shall be sound, clean, commercially straight and must not reveal injurious defects during forging, heat treating, or machining.

(b) Visual examination of deep acid etched bars in the as furnished condition shall show no evidence of abnormal segregation, pipes, cracks, seams, or abnormal change in structure from the surface to the center.

(c) Unless otherwise stated, finished parts are subject to magnetic inspection.