

 <i>An SAE International Group</i>	AEROSPACE RECOMMENDED PRACTICE	SAE ARP5369	REV. A
		Issued 1998-11 Reaffirmed 2004-12 Revised 2010-08	
		Superseding ARP5369	
Guidelines for Wire Identification Marking Using the Hot Stamp Process			

RATIONALE

The ARP is being updated during the 5 year review to remove reference to inactive standards and introduce reference to new standards.

FOREWORD

This SAE Aerospace Recommended Practice (ARP) is intended to serve as a guide toward standard practice and is subject to change to keep pace with experience and technical advances.

SAENORM.COM : Click to view the full PDF of arp5369a

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: http://www.sae.org

**SAE values your input. To provide feedback
on this Technical Report, please visit**
<http://www.sae.org/technical/standards/ARP5369A>

TABLE OF CONTENTS

1.	SCOPE	3
2.	REFERENCES	3
2.1	Applicable Documents	3
2.1.1	SAE Publications	3
2.1.2	U.S. Government Publications	3
2.2	Definitions	4
2.3	Symbols and Abbreviations	4
3.	REQUIREMENTS	4
3.1	Materials	4
3.2	Equipment	4
3.3	Maintenance	5
4.	QUALITY ASSURANCE PROVISIONS	5
4.1	Quality Control Inspection	5
4.2	Process Qualification Testing	6
5.	NOTES	7

SAENORM.COM : Click to view the full PDF of arp5369a

1. SCOPE

- 1.1 These guidelines have been written to provide process information regarding the hot stamp method of marking wire identification directly on aerospace wires and cables.
- 1.2 This document is not intended to encourage the use of hot stamp marking or to endorse the related process. This method of marking wire identification is prohibited on any aerospace vehicle wiring that is required to conform to the provisions of AS50881. Methods which do not deform wire or cable insulation, such as Ink Jet, Dot Matrix or UV Laser marking are encouraged as a means of minimizing the possibility of insulation damage, particularly on insulation constructions of less than 0.010 in wall thickness. AIR5575 provides a comprehensive report on the issue of wire damage than can occur when hot stamp wire marking process is employed.
- 1.3 In recognition that the present use of hot stamp wire marking is in some operations and may continue for an extended period, the guidelines provided in this document are intended to provide process control information necessary to minimize the possibility of insulation damage.

2. REFERENCES

2.1 Applicable Documents

The following publications form a part of this document to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of the other publications shall be the issue in effect on the date of the purchase order. In the event of conflict between the text of this document and references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

2.1.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AS1241	Fire Resistant Phosphate Ester Hydraulic Fluid For Aircraft
AS50881	Wiring, Aerospace Vehicle
AS4373	Test Methods For Insulated Electric Wire
ARP5607	Legibility of Print on Aerospace Wires and Cables
AIR5575	Hot Stamp Wire marking Concerns for Aerospace Vehicle Applications

2.1.2 U.S. Government Publications

Available from Document Automation and production Service (DAPS), Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, Tel: 215-697-6257, <http://assist.daps.dla.mil/quicksearch/>.

TT-I-735	Isopropyl Alcohol
MIL-PRF-5606	Hydraulic Fluid, Petroleum Base, Aircraft, Missile, and Ordnance
MIL-DTL-5624	Turbine Fuel, Aviation, Grade JP-4, JP-5, and JP-5/JP-8 ST
MIL-PRF-7808	Lubricating Oil, Aircraft Turbine Engine, Synthetic Base
MIL-DTL-83133	Turbine Fuel, Aviation, Kerosene Types, NATO F-34 (JP-8) and NATO F-35

2.2 Definitions

HOT STAMP MARKING: Hot stamp marking uses a heated typeface to transfer pigment from a ribbon or foil to the surfaces of wires or cables.

PRESSURE: In the context of this specification, pressure shall be interpreted as the pneumatic air pressure required to provide suitable force to the printhead to obtain acceptable markings.

DWELL TIME: The specific length of time that is required to mark each individual character on a wire or cable.

TEMPERATURE: In the context of this specification, temperature shall be interpreted as the machine setting for the heat applied during the marking process.

2.3 Symbols and Abbreviations

UV Ultraviolet

psi Pounds per square inch

3. REQUIREMENTS

3.1 Materials

3.1.1 Foils: A variety of types of marking foils are available from various manufacturers. The type of ribbon or foil to be used for a specific application is generally selected to provide compatibility with the manufacturer's marking equipment and the wire or cable's insulation material and construction. Resistance to abrasion and resistance to aircraft fluids can also vary with the type of foil used. The specific color of identification marking also affects the selection of foil types. Consult your wire marking equipment and foil manufacturers for product recommendations for specific applications.

CAUTION: The foils should be stored in accordance with the foil manufacturer's recommendations and not used after the stated shelf life has expired.

3.2 Equipment

3.2.1 Marking Machines: A variety of wire marking machines have been developed and are in use at various facilities. Each has specific attributes. These machines are generally adjustable in terms of marking temperature, pressure and dwell time.

CAUTION: Typewheels, marking type and fixtures must be selected on the basis of the outside diameter, not gauge, of the wire to be printed. The proper selection and sizing of these items is critical to achieving maximum efficiency of the printer with a minimum of insulation penetration. It is not recommended that the Hot stamp process be used on wire with outside diameters of less than 0.035 in.

3.2.2 Adjustments: Consult your wire marking equipment manufacturer for specific adjustments of the recommended temperature, pressure and dwell time settings for each type of wire insulation construction to be marked. It may be advisable to send examples of wire to be marked to the equipment manufacturer as a means of ensuring that appropriate machine settings are identified. This can be particularly helpful when new wire constructions are encountered. Wires of the same part number from different manufacturers will vary in their markability. Settings for temperature, pressure and dwell time may need to be frequently adjusted in order to maintain acceptable wire marking contrast and durability. With some insulation materials, adjustments may be required for each new reel of wire to be marked, even if the wire is of the same part number and manufacturer as the previously marked reel. The pressure necessary to obtain suitable print results is determined by the substrate being printed, the length of text to be applied and the condition of the equipment being used. In areas of high air demand, an air accumulator may be required in order to maintain print head pressure and assure consistent print quality.

- 3.2.3 Typewheels: The selection of appropriate typewheels is dependent on character height, width and radius, the type of marking equipment used, the durometer or resiliency of the wire insulation and the outside diameter of the wire to be marked.

CAUTION: To avoid insulation damage, it is recommended that curved face type be used on smaller diameter wires. Consult the specific manufacturer's instructions for recommended typewheels.

3.3 Maintenance

- 3.3.1 All printing equipment shall be kept clean. Dereeling apparatus for transporting wire between its reel or container and the marking equipment shall be inspected frequently to ensure that it is smooth running and free of surface irregularities, burrs, etc., which might damage wire or cable insulation. Regular maintenance of pneumatic systems is required so as to assure that a clean, dry air source providing 100 psi regulatable air is provided.

CAUTION: Typewheels and wire fixtures should be inspected regularly and replaced on an as needed basis to allow the best results when printing.

4. QUALITY ASSURANCE PROVISIONS

4.1 Quality Control Inspection

- 4.1.1 Frequency of Inspection: Tests and examinations of 4.1.2 and 4.1.3 shall be performed on an ongoing basis at such times and with such quantity of samples as specified by the wire marking processor's quality assurance activity. As a minimum, these examinations should be performed whenever a different reel of wire or cable is put on the machine, whenever adjustments have been made to pressure, temperature, or dwell time, and when any change to equipment or marking foils has taken place.
- 4.1.2 Legibility: All characters must be legible and completely understood at 15 inches $\pm$ 2 inches in an ambient light of 30 foot candles, nominal. The wire ID information must be clear without magnification other than spectacles or contact lenses and read error-free. For additional information see ARP5607: Legibility of Print on Aerospace Wires and Cables.
- 4.1.3 Mandrel Wrap Examination: A specimen of marked wire that is at least 12 in long shall be subjected to 5 cycles of bending at room temperature. One complete cycle shall consist of tightly winding the wire (5 loops minimum) around a mandrel, specified in Table 1, unwinding and reverse winding the wire. At least 1 marked pattern shall be on the outside of the wire during the wrapping. After the fifth cycle, there shall be no visible evidence of cracking, piercing, wrinkling or splitting of the insulation when subjected to magnification between 6 and 10 times in an ambient light of 30 ft candles. Specimens used for this test should not be used for installation on an aircraft.

TABLE 1 – BEND TEST MANDREL DIAMETERS

Wire Size	Mandrel Diameter (± 0.03 in)
26	0.125
24	0.125
22	0.250
20	0.250
18	0.250
16	0.375
14	0.500
12	0.500
10 and larger	10X wire outside diameter