REV B

AS85485™/10

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions

SAE Executive Standards Committee Rules provide that: " This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is

entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user'

RATIONALE

AS85485/10 IS BEING STABILIZED BECAUSE THE COMMITTEE DOES NOT ANTICIPATE FUTURE TECHNICAL CHANGES. FILTERLINE CABLES ARE CONSIDERED WELL-ESTABLISHED PRODUCTS. QUALIFIED SUPPLIERS ARE STILL MAINTAINED. REFERENCE CHANGES NOTED BY THE SUPPLIERS WHICH RESULTS IN A PRODUCT CHANGE WILL BE ADDRESSED BY A NEW REVISION.

STABILIZED NOTICE

THIS DOCUMENT HAS BEEN DECLARED "STABILIZED" BY THE SAE AE-8D WIRE AND CABLE COMMITTEE AND WILL NO LONGER BE SUBJECTED TO PERIODIC REVIEWS FOR CURRENCY. USERS ARE RESPONSIBLE FOR VERIFYING REFERENCES AND CONTINUED SUITABILITY OF TECHNICAL REQUIREMENTS. NEWER TECHNOLOGY MAY EXIST.

SALINORM. COM. Click to view the full PDF of asabakash Job STABILIZED 2021-06 **REVISED 2016-05** ED 2004-06 SSUI THIRD ANGLE PROJECTION For more information on this standard, visit https://www.sae.org/standards/content/AS85485/10B

CUSTODIAN: AE-8/AE-8D

AEROSPACE STANDARD

CABLE, ELECTRIC, FILTER LINE, SMALL DIAMETER, COMPONENT WIRE, SILVER-COATED HIGH-STENGTH COPPER ALLOY CONDUCTOR, RADIO FREQUENCY ABSORPTIVE, 150 °C, 600-VOLT

AS85485™/10

PROCUREMENT SPECIFICATION: AS85485

REV. В

Copyright © 2021 SAE International

NOTICE

THE COMPLETE REQUIREMENTS FOR PROCURING THE PRODUCT DESCRIBED HEREIN SHALL CONSIST OF THIS DOCUMENT AND THE LATEST ISSUE OF AS85485.




FIGURE 1 - AS85485/10 CONFIGURATION

TABLE 1 - CONSTRUCTION DETAILS

			DIAMETER <	FI	FINISHED WIRE		
		STRANDING	OF STRANDED	RESISTANCE			
		(NUMBER OF	CONDUCTOR	AT 20 °C (68 °F)	AT 20 °C (68 °F)		
	WIRE	STRANDS X AWG	(INCHES)	(OHMS/1000 FT)	DIAMETER	(LB/1000 FT)	
PART NO. <u>1</u> /	SIZE	GAUGE OF STRANDS)	(MIN) (MAX)	(MAX)	(INCHES)	(MAX)	
M85485/10-24-*	24	19 X 36	.023 .025	28.4	.045 ± .002	3.0	

1/ THE ASTERISK IN THE PART NUMBER COLUMN SHALL BE REPLACED BY COLOR CODE DESIGNATORS IN ACCORDANCE WITH AS85485 (SEE PIN BELOW).

TABLE PERFORMANCE DETAILS

	BEND TESTING						
	MANDREL DIAMETE	R	TEST LOAD				
	(INCHES) (±3%)		(LB) (±3%)				
	CROSSLINKING PROOF,	COLD	CROSSLINKING PROOF,	COLD			
	IMMERSION AND	BEND	IMMERSION AND	BEND			
PART NO. <u>1</u> (LIFE CYCLE TESTS	TEST	LIFE CYCLE TESTS	TEST			
M85485/10-24-*	.500	2.00	.625	3.00			

1/ THE ASTERISK IN THE PART NUMBER COLUMN SHALL BE REPLACED BY COLOR CODE DESIGNATORS IN ACCORDANCE WITH AS85485 (SEE PIN BELOW).



REQUIREMENTS: ALL REQUIREMENTS SHALL CONSIST OF THIS DOCUMENT AND THE LATEST ISSUE OF AS85485.

CONFIGURATION AND MATERIAL:

WIRE CONFIGURATION AND MATERIAL SHALL BE IN ACCORDANCE WITH FIGURE 1 AND TABLE 1.

RATINGS:

TEMPERATURE RATING: 150 °C (302 °F) MAXIMUM CONTINUOUS CONDUCTOR TEMPERATURE

VOLTAGE RATING: IN ACCORDANCE WITH AS85485

- 3. BLOCKING: 200 °C ± 3 °C (392 °F ± 5 °F) FOR 6 HOURS
- IDENTIFICATION MARKING:

PART IDENTIFICATION NUMBER (PIN) MARK SHALL BE AS FOLLOWS:



COMPONENT WIRE PIN MARKING: A COMPONENT WIRE PIN SUPPLIED AS A FINISHED PART SHALL BE MARKED ON THE OUTER SURFACE OF THE COMPONENT WIRE. THE PRIMARY JACKET COLOR CODE AND STRIPE CODE IS NOT REQUIRED, BUT IF INCLUDED ALL INFORMATION SHALL BE INCLUDED.

CABLE MARKING: COMPONENT WIRE USED AS A COMPONENT IN CABLE (I.E., 4\$85485/11 OR /12 CABLE) SHALL BE MARKED IN ACCORDANCE WITH THE CABLE REQUIREMENTS.

COMPONENT WIRE IDENTIFICATION MARKING AND COLOR STRIPE DURABILITY: 125 CYCLES (250 STROKES) (MIN), 500 GRAMS WEIGHT.

COLOR:

PRIMARY INSULATION - NATURAL FILTER LAYER - BLACK PRIMARY JACKET - LIGHT VIOLET

- 5. CONCENTRICITY: PRIMARY INSULATION 50% MINIMUM; FINISHED WIRE 70% MINIMUM
- 6. CROSSLINKING PROOF TEST: 7 HOURS AT 300 ± 3 °C (572 °F ± 5 °F) USING THE MANDRELS AND WEIGHT IN SPECIFIED TABLE 2.
- 7. FLAMMABILITY: 3 SECONDS MAXIMUM AND 3 INCHES MAXIMUM
- 8. HUMIDITY RESISTANCE: INSULATION RESISTANCE 5000 MEGOHMS FOR 1000 FEET MINIMUM
- IMMERSION: DIAMETER INCREASE PERMITTED SHALL BE 5% MAXIMUM. THERE SHALL BE NO CRACKING, OR DIELECTRIC BREAKDOWN (VOLTAGE WITHSTAND) WHEN SUBJECTED TO THE BEND TEST WITH THE WEIGHT AND MANDREL SIZES SPECIFIED IN TABLE 2.
- 10. INSULATION ELONGATION AND TENSILE STRENGTH (PRIMARY INSULATION, FILTER LAYER, AND JACKET SHALL BE PULLED TOGETHER):

ELONGATION – 50% MINIMUM TENSILE STRENGTH – 3000 LBF/ IN² MINIMUM

11. INSULATION FLAWS:

PRIMARY INSULATION ONLY:

SPARK TEST; 1.5 KILOVOLTS (RMS), 60 Hz IMPULSE DIELECTRIC TEST; 6.0 KILOVOLTS (PEAK)



AEROSPACE STANDARD

FINISHED WIRE:

SPARK TEST; 3.0 KILOVOLTS (RMS), 60 Hz IMPULSE DIELECTRIC TEST; 8.0 KILOVOLTS (PEAK)

- 12. INSULATION RESISTANCE: 5000 MEGOHMS FOR 1000 FEET MINIMUM
- 13. INSULATION THICKNESS:

PRIMARY INSULATION; .002 INCH MINIMUM FILTER LAYER; AVERAGE .0025 INCH MINIMUM PRIMARY JACKET: .0035 INCH MINIMUM

- 14. LIFE CYCLE: 168 HOURS AT 200 °C ± 3 °C (392 °F ± 5 °F). THERE SHALL BE NO CRACKING OR DIELECTRIC BREAKDOWN (VOLTAGE WITHSTAND) WHEN SUBJECTED TO THE BEND TEST WITH THE WEIGHT AND MANDREL SIZES SPECIFIED IN TABLE 2.
- 15. LOW TEMPERATURE-COLD BEND: -65 °C ± 2 °C (-85 °F ± 4 °F) FOR 4 HOURS. THERE SHALL BE NO CRACKING OR DIELECTRIC BREAKDOWN (VOLTAGE WITHSTAND) WHEN SUBJECTED TO THE BEND TEST WITH THE WEIGHT AND MANDREL SIZES SPECIFIED IN TABLE 2.
- 16. SHRINKAGE: .125 INCH MAXIMUM AT 200 °C ± 3 °C (392 °F ± 5 °F)
- 17. SMOKE: 200 °C ± 2 °C (392 °F ± 4 °F), NO VISIBLE SMOKE
- 18. SURFACE RESISTANCE: 500 MEGOHM INCHES MINIMUM, INITIAL AND FINAL READINGS
- 19. THERMAL SHOCK RESISTANCE: OVEN TEMPERATURE, 150 °C ± 3 °C (302 °F ± 5 °F). THEMAXIMUM CHANGE IN MEASUREMENTS SHALL BE .060 INCH.
- 20. VOLTAGE WITHSTAND (POST-ENVIRONMENTAL): 1500 VOLTS (RMS) 60 Hz
- 21. WRAP TEST: 6 HOURS AT 200 °C ± 3 °C (392 °F ± 5 °F); NO CRACKING
- 22. ATTENUATION: THE WIRE ATTENUATION SHALL BE IN ACCORDANCE WITH TABLE 3 WHEN TESTED IN A AS85485/12 ONE COMPONENT WIRE, TIN-COATED COPPER SHIELDED CONFIGURATION (SEE APPLICATION NOTE)

TABLE 3 - ATTENUATION (INSERTION LOSS)

NAOE 40 4/4	12 ONE CONDUCTOR	DACC DAND			TDANCITION DAND			CTOD DAND
IVI85484/	PASS BAND		TRANSITION BAND			STOP BAND		
CC	(dB/ft)		(dB/ft)			(dB/ft)		
WIRE SIZE	WIRE TYPE	1.0	10	0.0	100	500	1000	1 TO 12
		MHz	MHz		MHz	MHz	MHz	GHz
		(MAX)	(MIN)	(MAX)	(MIN)	(MIN)	(MIN)	(MIN)
-24	AS85485/10.	.02	.06	.20	1.3	12	30	30

- 23. THERMAL STABILITY: 1250 HOURS AT 180 °C ± 3 °C (356 °F ± 5 °F). THE SAMPLE SHALL BE M85485/12 ONE COMPONENT TIN COATED COPPER SHIELDED CONFIGURATION IN CONDUCTOR SIZE 24. AFTER EXPOSURE THE VOLTAGE WITHSTAND (DIELECTRIC) SHALL BE 1500 VOLTS (RMS) 60 Hz AND THE STOP BAND ATTENUATION SHALL BE AS SPECIFIED IN TABLE 3.
- 24. QUALIFICATION SAMPLE: TWO SPECIMENS ARE REQUIRED. ONE SPECIMEN SHALL INCLUDE THE PIN MARKING AND ONE SPECIMEN SHALL INCLUDE THE STRIPE MARKING. EITHER SPECIMEN MAY BE USED TO COMPLETE THE REMAINING AS85485 QUALIFICATION REQUIREMENTS.

