



400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION

MAM 2243B

Issued 7-15-80  
Revised 1-1-90

Superseding MAM 2243A

Submitted for recognition as an American National Standard

## TOLERANCES, METRIC Corrosion and Heat Resistant Steel Tubing

1. **SCOPE:** This specification covers manufacturing tolerances applicable to seamless and welded tubing of corrosion and heat resistant steel ordered to metric dimensions. These tolerances apply to all conditions and are based on individual measurements, unless otherwise noted. Tubing may be specified by two dimensions only (OD and wall thickness, ID and wall thickness, or OD and ID).

- 1.1 These tables are based on logical metric values and preferred metric sizes.
- 1.2 Throughout this specification the term "metric" is intended to refer to the SI system.
- 1.3 AMS 2243, specified in inch/pound units, is the equivalent of this MAM.

2. **DIAMETER:**

- 2.1 Tubing Other than Pressure Tubing: Welded (See 2.1.1) or Seamless (See 2.1.2):

TABLE I

Specified OD or ID Millimetres	Tolerance, Millimetre Including Ovality (See 2.3) Plus and Minus
Up to 14, excl	0.10
14 to 38, excl	0.10
38 to 90, excl	0.20
90 to 140, excl	0.30
140 and over	0.75

- 2.1.1 Welded Tubing: Shall be bead-reduced or shall be cold finished by tube-reducing, cold-drawing, machining, or grinding.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.2 Seamless Tubing: Shall be cold-finished by tube-reducing, cold-drawing, machining, or grinding.

2.2 Pressure Tubing (See 6.1.5); Cold Drawn or Cold Reduced (Seamless or Welded):

TABLE II

Specified OD or ID Millimetres	OD or ID Tolerance, Millimetres Including Ovality (See 2.3) Plus and Minus
Up to 14, incl	0.08
Over 14 to 25, excl	0.10
25 to 38, excl	0.13
38 to 50, excl	0.15
50 to 65, excl	0.18
65 to 90, excl	0.25
90 to 140, excl	0.40
140 to 200, excl	0.75
200 to 215, incl	1.12

2.2.1 Half Tolerances: When half tolerances are specified, the tolerances of Table II shall be plus only; the minus side of the tolerance range shall not be applicable.

2.3 Ovality, All Tubing: All of the tolerances shown in Tables I and II include ovality except on light-walled tubing where the specified wall thickness is 3% or less of the specified OD. On such light-walled tubing, there is an additional ovality tolerance (in addition to the tabular tolerances) equal to  $\pm 0.5\%$  of the specified OD (or ID); however, the average diameter shall be within the tabular tolerances.

### 3. WALL THICKNESS:

3.1 Tubing Other than Pressure Tubing; Welded or Seamless:

TABLE III

Specified OD or ID Millimetres	Wall Thickness Tolerance, % Plus or Minus	
	For Wall Thickness, Millimetres, Shown Under 6.0	6.0 and Over
Up to 14, excl	15	15
14 to 38, excl	12.5	10
38 to 90, excl	12.5	10
90 to 140, excl	12.5	10
140 and Over	12.5	10

3.2 Pressure Tubing (See 6.1.5); Seamless or Welded: Shall be  $\pm 10\%$  for all specified diameters.

3.2.1 Half Tolerances: When half tolerances are specified, tolerance shall be  $\pm 10\%, -0\%$ .